

DINITROL 81 Aerosol

Universal Protection

Characteristics:

- Milky Transparent
- Tack free
- Wax film
- Against galvanic corrosion
- Permanent or temporary
- Thixotropic

Applications:

On evaporation of the solvent, DINITROL 81 Aerosol leaves a transparent, hard and waxy film, ideally suited as a protective coating, affording easy visual inspection of the metal surface, reading of labels, numbers, etc.

DINITROL 81 Aerosol is intended for protection, in storage and in transit, of finished surfaces of steel and of other metals, particularly when a colourless, transparent and tack-free film is desired. DINITROL 81 Aerosol may also be used for protection of lacquered surfaces withstanding white spirit and similar solvents, e.g. different types of tooling and equipment engines and vehicles.

Method of use:

DINITROL 81 Aerosol is applied by spraying with the can at approximately 30 cm off the object. The ideal temperature for the application is 15 – 20°C. During warehousing, application and drying, the measures to be taken are the same as those applying to paints and lacquers.

Technical properties:

Colour:	transparent
Type of film:	waxy
Density at 20°C:	720 kg/m ³
Dry matter content (conc.):	7,9% by weight
Flash point:	< -20°C
Aromatic content in solvent:	< 0,5%
Rec film thickness:	10 µm
Drying time:	30 min.
Effect on car paint:	none
Removability:	Hydrocarbon solvents

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com