

DINITROL Activator Plus

Adhesion promoter for glass bonding on windshields and backlites

Characteristics:

The DINITROL Activator Plus is a solvent containing adhesion promoting formulation. It's specifically formulated for the pre-treatment of bond faces in direct glazing work prior to application of various DINITROL polyurethane adhesives. DINITROL Activator Plus improves adhesion on glass, ceramic-coated glass, the cut face of old polyurethane adhesive, polyurethane pre-applied windows glass and paints.

Application:

The bonding area on the windshields must be clean and free of any residues. For the cleaning we recommend the cleaning agent DINITROL 582. The DINITROL Activator Plus should be applied by the wipe on/wipe off procedure, i.e. in the first step the activator should be wiped on the glass-ceramic surface of the windshield by a tissue, dauber or cotton ball, wetted with the activator. In a second step a residual excess on the surface should be taken off by wiping with a clean tissue. Due to its reactivity with moisture, the opened bottle has to be used within a few days. After this time, or if the DINITROL Activator Plus has become milky instead of clear/slightly yellowish, the product must be discarded. An inactivity of the activator is possible. This product is suitable for experienced professional users only.

Further information:

The following publications are available on request:

- Safety data sheet
- DINOL pre-treatment chart

Health and safety / storage:

According to 1907 / 2006 EC, DINITROL Activator Plus has to be labelled as flammable and irritant. Symbol: F, Xn, N
Store between 0 and 35°C, in closed packaging in a dry and ventilated area.

Available packagings:

Bottle 30 ml Bottle 100 ml

Technical properties:

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com

DINITROL Activator Plus

Adhesion promoter for glass bonding on windshields and backlites

Chemical base:	alcoholic solvents adhesion promoter
Colour:	clear, slightly yellowish
Density:	800 ± 30 kg/m ³
Viscosity Brookfield:	1 – 5 mPa·s
Drying time:	> 5 Min.
Flash point:	< 21°C
Application temperature:	+5°C – 40°C
Coverage:	approx. 50 g/m ²
Application method:	tissue / paper "wipe on / wipe off"
Flash-off time:	min. 5 minutes max. 24 hours
Shelf life:	12 month

¹⁾ 23°C / 50% rf

Health and safety information can be obtained from the material safety data sheet and the product label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
 Pyrmonter Str. 76
 D-32676 Lügde
 Telefon:
 +49 (0) 52 81 / 9 82 98-0
 Telefax:
 +49 (0) 52 81 / 9 82 98-60
 E-Mail:
 service@dinol.com